

# PAINTMASTER (2000) LIMITED

HEAD OFFICE:-

UNITS 12 – 17, BINGSWOOD INDUSTRIAL ESTATE,  
WHALEY BRIDGE, HIGH PEAK, DERBYSHIRE, SK23 7LY

TELEPHONE: 01663-733633 FAX: 01663-735366

## DATA SHEET

### ALKYD QUICK DRYING FLOOR PAINT

A premium quality, quick-drying, acrylic alkyd floor enamel. One coat covers most previously painted surfaces that are in fair to good condition.

- ) Resistant to soaps and detergents, grease and oil.
- ) Easy to apply.
- ) Exhibits a smooth, uniform appearance.
- ) One coat covers most previously painted surfaces that are in fair to good condition.
- ) Appropriate for use in hazardous areas.

**Recommended For: Limitations:**

- Garage Floors: Many tyres contain compounds which may attack latex paints, resulting in loss of adhesion and film pickup.  
Protect tyre lanes by driving over mats or runners.
- Do not apply to bare wood.
- CAUTION: All floor enamels may become slippery when wet. Where non-skid characteristics are desired, a small amount of Anti-Slip Aggregate may be added.
- Do not apply when air and surface temperatures are below 50°F (10°C).
- New concrete requires acid etching.

**Colors: —Standard:**

Grey, Lt Grey, and Red

**Certification:**

Formulated without lead, mercury, or chromates. Very low in VOCs.

For interior and exterior use on asphalt, unpainted concrete (new or old) and previously finished wood or concrete floors.

Particularly recommended for basements, porches, patios, breezeways, garages, showrooms, and industrial applications.

**Technical Data**

Vehicle Type Alkyd Acrylic Latex

Pigment Type. Titanium Dioxide

Volume Solids. 30%

Theoretical Coverage At Recommended Film Thickness 70-100 sq ft per litre.

*Depending on surface texture and porosity*

*Be sure to estimate the right amount of product for the job. This will ensure color uniformity and minimize the disposal of excess paint.*

Recommended Film Thickness – Wet 2.9 mils – Dry 0.9 mils

Dry Time @ 77°F — Set To Touch 1 Hour (25°C)

@ 50% RH — Dry To Touch 4 Hours

— To Recoat Overnight

— To Service 24 Hours

Dries By Evaporation, Coalescence Viscosity.  $78 \pm 2$  KU

Flash Point (Seta) None 60° Specular Gloss Pearl

Surface Temperature at application – Min. 50°F – Max. 90°F

Thin With Clean Water Clean Up Thinner Clean Water

Storage Temperature – Min. 40°F – Max. 90°F

Volatile Organic Compounds (VOC) *Unthinned, this product is formulated not to exceed 400 Grams/Liter. \*\**

### **Product Information**

#### **Surface Preparation**

To insure adhesion and durability, prepare the surface properly. It must be clean and free of all wax, grease, oil, dirt, loose or flaking material, acid substance and soap deposits. To clean floor, scrub with a detergent or solution of 1/2 cup trisodium phosphate per gallon of water; flush well with clean water. Glossy painted surfaces must be dulled. Smooth, hard-troweled concrete floors should be acid-etched before painting. Acid suitable for etching should be labeled with directions and precautions; observe them carefully.

**NOTICE:** Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator and proper containment and cleanup.

#### **Primer/Finish Systems**

##### **Unpainted Concrete:**

Thin first coat with 1 pint water per gallon of paint and brush well into surface. Allow to dry overnight; then apply finish coat liberally, without thinning, by brush or roller.

##### **Previously Painted Wood and Concrete:**

Apply first coat, without thinning, to properly prepared surface. For maximum

durability, add a second coat after an overnight dry.

### **Application**

**Mixing of Paint:** Stir thoroughly before and occasionally during use. Apply with a quality synthetic brush, short or medium nap roller, pad, or spray. Do not apply when air and surface temperatures are below 50°F (10°C).

### **Thinning/Cleanup**

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents. Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program.

### **CAUTION! Contains Ethylene Glycol**

CAUSES EYE IRRITATION.

**Use only with adequate ventilation.** Do not breathe vapors, spray mist or sanding dust. Avoid contact with eyes and prolonged or repeated contact with skin. Wear eye protection and gloves during application or sanding. Close container after each use.

**FIRST AID:** If affected by inhalation of vapors or spray mist, remove to fresh air. In case of eye contact, flush immediately with plenty of water for at least 16 minutes and call a doctor; for skin, wash thoroughly with soap and water. In case of ingestion, DO NOT INDUCE VOMITING. Get medical help immediately.

**IN CASE OF SPILL:** Absorb with inert material and dispose of as specified under **Thinning/Cleanup**.

**KEEP OUT OF REACH OF CHILDREN**

**PROTECT FROM FREEZING**